

GLASS FIBER GEOGRID

| Properties | Unit | GTF - G03 | TEST METHOD |
|-----------------------------|--|--------------|-------------|
| Tensile Strength (MD x CMD) | kN/m (≥) | 100 x 200 | ASTM D 6637 |
| Tensile Elongation | % | 3 (± 1) | |
| Young's Modulus E | MPa | 73000 | |
| Melting Point Coating | ° C (>) | 250 | ASTM D 276 |
| Mass per Unit Area | g/m ² (>) | 610 | ASTM D 5261 |
| Aperture Size | mm | 12.5 x 12.5 | |
| Roll Width | mtr. | Up to 5 Mtr. | |
| Roll Length | mtr. | 50 / 75 | |
| Material | Glassfiber Geogrid Coated with Asphalt Compatible proprietary Chemical along with One Side PSA | | |

MD - Machine Direction

CMD - Cross Machine Direction

PSA - Pressure Sensitive Adhesive Backing

- The values given are indicative and correspond to average results obtained in our Laboratories and testing institutes.
- The right is reserved to make changes without notice at any time.

